

MAIN PRODUCT-PROPERTIES

- In coating systems with WIESTRUCTAN-ACU as high-grade electrical conductive coating system according to TRBS 2153
- The requirements for electrical surface resistances according to EN 60079-0, chapter 26.13 are met in the system
- Ground conductivity according to EN 1081: $R_2=10^4$ to $10^6 \Omega$
- Application areas: ATEX and special machines for avoiding electrostatic charging

PRODUCT DATA

GEHOPON-C0009A-Metallgrund, mat



C0009A-750 Dark grey (other colours on request)




Mixing ratio by weight
7:1 with curing agent EX-4



Thinner V-538

GEHOPON-C0009A-Metallgrund / Guideline

	Density (g/mL)	Solid content (weight %)	VOC-content (weight %)	Solid content by volume	
	1.25	59.0	41.0	(%)	(mL/kg)
	DFT* (µm)	Calculated wet-film thickness (µm)	Consumption (kg/m ²)	Spreading rate (m ² /kg)	
	60	146	0.180	5.5	

COMMENTS ON PROCESSING

Recommendation at temperatures of approx. 20 °C



Airmix



High pressure



Roller/Brush application




Application viscosity (s) (8 mm DIN-cup)	10 to 15	6 to 8	10 to 20
Nozzle diameter (mm)	0.33 to 0.43	1.5 to 2.0	-
Material pressure (bar)	150 to 200	-	-
Atomiser pressure (bar)	1.5 to 2.5	3.0 to 4.0	-
DFT* per working operation (µm)	60 to 80	60 to 80	40 to 60
Addition of thinner (%)	2 to 5	10 to 15	0 to 5



Pot life

6 to 8 hours (relating to 20 to 25 °C)

* DFT = Dry Film Thickness

Drying/Curing times at 60 µm DFT		Ambient air temperature 20 °C
	touch dry:	after approx. 30 minutes
	tack free:	after 4 to 5 hours
	ready for overcoating/handling:	after 12 to 16 hours

INSTRUCTIONS FOR APPLICATION

Surface preparation

Steel surfaces and cast iron

- Remove adhesion-reducing substances e. g. cleaning, washing, phosphating
- Blast-cleaning Sa 2 1/2 according to EN ISO 12944-4, Roughness grade medium (G) according to EN ISO 8503-1

Hot-dip-galvanised steel surfaces and aluminium/cast aluminium

- Remove adhesion-reducing substances, e. g. cleaning, washing
- At natural weathering or condensation:
Sweep blast-cleaning according to EN ISO 12944-4.
After sweep blast-cleaning the surface shall have a uniform dull appearance.
- Chemical conversion layer (chromate, chromate free, phosphating)



Air and surface temperature

optimal at 15 to 25 °C, not below 5 °C, not over 40 °C



max. 80 % relative humidity

PAINT SYSTEMS

EXAMPLES

		Product(s) (other paint systems on request)
	Priming coat	GEHOPON-C0009A-Metallgrund
	Monolayer	WIESTRUCTAN-ACU, M4-... mat, conductive

SAFETY MEASURES



The relevant data can be found in the current material safety data sheets, available at www.geholit-wierner.de.

The statements made here are based on the present state of our knowledge. We do not assume liability for damages resulting from the use of the material or from any advice given by our employees. In this respect, any advice given by our employees has to be seen as not binding. The processor is responsible for the supervision or construction, the maintaining of process guidelines and the observation of the established rules of techniques, even if our employees are present at the time our material is being applied. This information is subject to modifications due to technical improvements. The latest edition of this information replaces all previous issues.