

MAIN PRODUCT PROPERTIES

- Flat, waterborne monolayer based on alkyd resin for nominal dry film thicknesses of 80 to 100 µm
- In combination with optional GEHOTEX-W90-Metallgrund as a high-grade, elastic 1-pack coating system for machines, plants etc.

PRODUCT DATA

GEWITEX-W143, flat



W143T-F.... (RAL colours, other colours on request)




Mixing ratio by weight

Not relevant



Demineralised water

GEWITEX-W143T / Guide values

	Density (g/mL)	Solid content (weight %)	VOC content (weight %)	Solid content by volume	
				(%)	(mL/kg)
	1.30	58.5	< 3	46.0	355
	DFT * (µm)	Calculated wet-film thickness (µm)	Consumption (kg/m²)	Spreading rate (m²/kg)	
	80	170	0.225	4.4	

PROCESSING INSTRUCTIONS

Recommendation at
temperatures
of approx. 20 °C



Airmix



Airless ¹⁾



**High
pressure**

	Airmix	Airless ¹⁾	High pressure
Application viscosity (s) (8 mm DIN-cup)	25 to 30	25 to 30	10 to 15
Nozzle diameter (mm)	0.33 to 0.38	0.33 to 0.38	1.3 to 1.5
Material pressure (bar)	150 to 250	200 to 300	-
Atomiser pressure (bar)	2.5 to 3.5	-	3.0 to 4.0
DFT * per working operation (µm)	80 to 100	80 to 100	80 to 100
Addition of thinner (%)	0	0	3 to 5




¹⁾ only conditionally recommended



Pot life

Not relevant

* DFT = Dry Film Thickness

Drying/Curing times at 80 µm DFT		Ambient air temperature 20 °C
	touch dry:	after approx. 90 minutes
	tack free:	after approx. 3 hours
	ready for overcoating/handling:	after approx. 12 hours

INSTRUCTIONS FOR APPLICATION

Surface preparation

Steel surfaces and cast iron

- Remove adhesion-reducing substances e. g. cleaning, washing, phosphating
- Blast cleaning Sa 2 ½ according to EN ISO 12944-4, Roughness grade medium (G) according to EN ISO 8503-1

Optional Primer (see below)

- Remove adhesion-reducing substances, e. g. cleaning, washing
- Before overcoating of other priming coats compatibility tests are recommended



Air and surface temperature

optimal at 15 to 25 °C, not below 10 °C, not above 40 °C



max. 80 % relative humidity

PAINT SYSTEMS

EXAMPLES

		Product(s) (other paint systems on request)
	Optional priming coat	GEHOTEX-W90-Metallgrund
	Monolayer / Top coat	GEWITEX-W143T

SAFETY MEASURES



The relevant data can be found in the current material safety data sheets, available at www.geholit-wierner.de.

The statements made here are based on the present state of our knowledge. We do not assume liability for damages resulting from the use of the material or from any advice given by our employees. In this respect, any advice given by our employees has to be seen as not binding. The processor is responsible for the supervision or construction, the maintaining of process guidelines and the observation of the established rules of techniques, even if our employees are present at the time our material is being applied. This information is subject to modifications due to technical improvements. The latest edition of this information replaces all previous issues.