

MAIN PRODUCT PROPERTIES

- 2-pack PUR high-solid primer mainly for wet-on-wet application with suitable high-gloss top coat
- Overcoatable wet-on-wet with WIEREGEN-M77N or WIEREGEN-M177 after approx. 15 minutes and with a wet film thickness of up to 75 µm
- Typical application areas: building machines, mobile cranes, ACE with high optical demands

PRODUCT DATA

WIEREGEN-D177-Metallgrund



D177-701 Silver grey
(other colours on request)




Mixing ratio by weight

5,4:1 with curing agent DX-77N



Thinner V-77N

WIEREGEN-D177-Metallgrund / Guide values

	Density (g/mL)	Solid content (weight %)	VOC-content (weight %)	Solid content by volume	
				(%)	(mL/kg)
	1.35	77.5	22.5	66.0	490
	DFT * (µm)	Calculated wet-film thickness (µm)	Consumption (kg/m ²)	Spreading rate (m ² /kg)	
	50	75	0.105	9.5	

PROCESSING INSTRUCTIONS

Recommendation at
temperatures
of approx. 20 °C



Airmix



High
pressure



Roller/Brush
application ¹⁾

Application viscosity (s)	30 to 40	30 to 40	30 to 40
Wet-on-wet application (s) (4 mm DIN cup)	20 to 25	20 to 25	-
Nozzle diameter (mm)	0.28	1.3 to 1.5	-
Spraying angle (degree)	40 to 60	-	-
Material pressure (bar)	120 to 150	-	-
Atomiser pressure (bar)	3.0 to 4.0	3.0 to 4.0	-
DFT ²⁾	35 to 60	35 to 60	35 to 60
Wet-on-wet application: WFT ³⁾ per working operation (µm)	60 to 75	60 to 80	-
Addition of thinner (%)	-	-	-
Wet-on-wet application	8 to 10	8 to 10	-






Pot life

45 to 60 minutes (at temperatures of 20 to 25 °C)

¹⁾ only recommended for small surfaces; formation of a product-specific surface structure is possible

²⁾ DFT = Dry Film Thickness

³⁾ WFT = Wet Film Thickness

Drying/curing times at 50 µm DFT with thinner V-77N		Ambient air temperature 20 °C
	touch-dry:	after approx. 30 minutes
	tack-free:	after approx. 6 hours
	ready for overcoating with WIEREGEN-M77 or WIEREGEN-M177 dry to handle:	after approx. 15 minutes after approx. 12 hours

INSTRUCTIONS FOR APPLICATION

Surface preparation

Steel surfaces and cast iron

- Remove adhesion-reducing substances e.g. cleaning, washing, phosphating
- Blast cleaning Sa 2 ½ according to EN ISO 12944-4, roughness grade medium (G) according to EN ISO 8503-1

Hot-dip galvanised steel surfaces and aluminium/cast aluminium

- Remove adhesion-reducing substances, e. g. cleaning, washing
- At natural weathering or condensation load:
Sweep blast cleaning according to EN ISO 12944-4.
After sweep blast cleaning, the surface must have a uniformly dull appearance.
- Chemical conversion layer (chromate, chromate free, phosphating)



Air and surface temperature

optimal at 15 to 25 °C, not below 10 °C, not above 40 °C



max. 80 % relative humidity

PAINT SYSTEMS

EXAMPLES

	Product(s) (other paint systems on request)
 Priming coat	WIEREGEN-D177-Metallgrund
Top coat	WIEREGEN-M77N WIEREGEN-M177

SAFETY MEASURES



The relevant data can be found in the current material safety data sheets, available at www.geholit-wiemer.de.

The statements made here are based on the present state of our knowledge. We do not assume liability for damages resulting from the use of the material or from any advice given by our employees. In this respect, any advice given by our employees has to be seen as not binding. The processor is responsible for the supervision or construction, the maintaining of process guidelines and the observation of the established rules of techniques, even if our employees are present at the time our material is being applied. This information is subject to modifications due to technical improvements. The latest edition of this information replaces all previous issues.