

**WIEREGEN-D80-Compact**  
- hints for application -

Coating system for pavements  
(film thickness 6 to 10 mm) according to ZTV-RHD-ST

Pos.	Products and services	Theoretical consumption (kg/m <sup>2</sup> )																			
1	<p><b>Surface preparation</b></p> <p>Blast-cleaning in surface preparation grade Sa 2 ½ according to EN ISO 12944-4. The priming coat should be applied immediately after blast-cleaning.</p>																				
2	<p><b>Priming coat</b></p> <p><b>GEHOPON-E24-Metallgrund</b> based on 2C-Epoxy-Zinc phosphate</p> <p><b>Nominal dry film thickness: 80 µm</b> The priming coat must not be scattered.</p> <table border="1"> <thead> <tr> <th>Processing times</th> <th>at +12 °C</th> <th>at +30 °C</th> </tr> </thead> <tbody> <tr> <td>Pot life / processability</td> <td>12 h</td> <td>6 h</td> </tr> <tr> <td>Water resistance after</td> <td>approx. 24 h</td> <td>approx. 12 h</td> </tr> <tr> <td>Over-coating after</td> <td>min. 24 h</td> <td>min. 8 h</td> </tr> </tbody> </table>	Processing times	at +12 °C	at +30 °C	Pot life / processability	12 h	6 h	Water resistance after	approx. 24 h	approx. 12 h	Over-coating after	min. 24 h	min. 8 h	<p>theoretical: 0.225 practical: 0.3 bis 0.5</p>							
Processing times	at +12 °C	at +30 °C																			
Pot life / processability	12 h	6 h																			
Water resistance after	approx. 24 h	approx. 12 h																			
Over-coating after	min. 24 h	min. 8 h																			
3	<p><b>RHD-pavements</b></p> <table border="0"> <tr> <td style="text-align: center;"><u>Single-layer system</u></td> <td style="text-align: center;"><u>Two-layer system</u></td> </tr> <tr> <td style="vertical-align: top;"> <p><b>WIEREGEN-D80-Compact</b> grey, D80-7201 based on 2C-Polyurethane 1 : 1 filled with quartz sand with a grain size of 1 to 3 mm</p> </td> <td style="vertical-align: top;"> <p>Scatter the fresh coating with quartz sand with a grain size of 1 to 3 mm</p> <p>After 24 h at 20 °C (96 h at 12 °C) apply the second layer</p> <p>Scatter the fresh coating in excess with quartz sand with a grain size of 1 to 3 mm</p> </td> </tr> </table> <table border="1"> <thead> <tr> <th>Processing times</th> <th>at +12 °C</th> <th>at +30 °C</th> </tr> </thead> <tbody> <tr> <td>Pot life / processability</td> <td>60 min</td> <td>30 min</td> </tr> <tr> <td>Water resistance after</td> <td>approx. 36 h</td> <td>approx. 16 h</td> </tr> <tr> <td>Over-coating after</td> <td>min. 5 d</td> <td>min. 24 h</td> </tr> <tr> <td></td> <td colspan="2" style="text-align: center;">max. 3 months</td> </tr> </tbody> </table>	<u>Single-layer system</u>	<u>Two-layer system</u>	<p><b>WIEREGEN-D80-Compact</b> grey, D80-7201 based on 2C-Polyurethane 1 : 1 filled with quartz sand with a grain size of 1 to 3 mm</p>	<p>Scatter the fresh coating with quartz sand with a grain size of 1 to 3 mm</p> <p>After 24 h at 20 °C (96 h at 12 °C) apply the second layer</p> <p>Scatter the fresh coating in excess with quartz sand with a grain size of 1 to 3 mm</p>	Processing times	at +12 °C	at +30 °C	Pot life / processability	60 min	30 min	Water resistance after	approx. 36 h	approx. 16 h	Over-coating after	min. 5 d	min. 24 h		max. 3 months		<p>approx. 0.925 per mm approx. 0.925 per mm</p> <p>Total consumption: 10 to 12 kg; approx. 5 kg remain</p> <p>approx. 0.925 per mm approx. 0.925 per mm</p> <p>Total consumption: 10 to 12 kg; approx. 5 kg remain</p>
<u>Single-layer system</u>	<u>Two-layer system</u>																				
<p><b>WIEREGEN-D80-Compact</b> grey, D80-7201 based on 2C-Polyurethane 1 : 1 filled with quartz sand with a grain size of 1 to 3 mm</p>	<p>Scatter the fresh coating with quartz sand with a grain size of 1 to 3 mm</p> <p>After 24 h at 20 °C (96 h at 12 °C) apply the second layer</p> <p>Scatter the fresh coating in excess with quartz sand with a grain size of 1 to 3 mm</p>																				
Processing times	at +12 °C	at +30 °C																			
Pot life / processability	60 min	30 min																			
Water resistance after	approx. 36 h	approx. 16 h																			
Over-coating after	min. 5 d	min. 24 h																			
	max. 3 months																				

**WIEREGEN-D80-Compact**  
**- hints for application -**

**Comments on consumption and determination of dry film thickness**

- The full scattering goes down in the total dry film thickness with 1 to 2 mm.
- We recommend, at a given nominal dry film thickness of e. g. 6 mm (for the whole coating) to calculate with a dry film thickness *without* scattering of approx. 5 mm (as  $5 \times 1.85 \text{ kg/m}^2 = 9.25 \text{ kg/m}^2$  of mixture WIEREGEN-D80-Compact plus supplement).
- The measurement of the dry film thickness must be carried out in accordance with ZTV-RHD-ST, in such a way that half the diameter of the maximum grain size must be subtracted from the measured value above the scattering (then 1.5 mm for chrome-ore slag).
- For calculation it has to be considered, that irregularities, such as roughness in the sheet metal, at the weldings and in the layer itself, considerable additional consumptions amounts compared to the theoretical consumption amounts related to the nominal dry film thickness can occur. (s. ZTV-RHD-ST item 5.4)

**Comments on processing**

Please also note the appropriate technical information for the priming coat GEHOPON-E24-Metallgrund.

**Mixing**

Mix GEHOPON-E24-Metallgrund homogeneously with the appropriate packaged curing agent EX-4. After a waiting period of 15 minutes stirr again and the mixture is ready to use.

Mix WIEREGEN-D80-Compact with the appropriate packaged curing agent DX-16. After repotting, add the respective supplements and mix thoroughly and homogeneously in a mechanical stirrer (compulsory stirrer). The material is then ready for use.

**Application methods**

GEHOPON-E24-Metallgrund: (Airless-)spraying, roller coating, brush application. Adjustment of processing viscosity with thinner V-538.

WIEREGEN-D80-Compact can be applied by trowel or wide spatula.

**Revision after longer waiting period**

If the maximum waiting period between the individual films specified on page 1 or in the technical information are exceeded, please ask the manufacturer. We generally recommend:

GEHOPON-E24-Metallgrund: grinding / sweeping and cleaning; if applicable apply additional priming coat.

WIEREGEN-D80-Compact: cleaning, e. g. by water jet

**Cleaning of equipment**

GEHOPON-E24-Metallgrund: thinner V-538

WIEREGEN-D80-Compact: thinner V-74

Cured material must be removed mechanically.

The statements made here are based on the present state of our knowledge. We do not assume liability for damages resulting from the use of the material or from any advice given by our employees. In this respect, any advice given by our employees has to be seen as not binding. The processor is responsible for the supervision of construction, the maintaining of process guidelines and the observation of the established rules of techniques, even if our employees are present at the time our material is being applied.

This information is subject to modifications due to technical improvements. The latest edition of this information replaces all previous issues.