


## MAIN PRODUCT-PROPERTIES

- At industrial production process also usable as a monolayer at low corrosion stress
- Together with suitable priming coats for high-grade paint systems also for high corrosion stress up to C5 according to EN ISO 12944-2
- Before overcoating of fully cured coatings with WIEREGEN-DW54 grinding is recommended

## PRODUCT DATA



2923/2023  
Certificate No:  
LR22163088MB

### WIEREGEN-DW54, flat



DW54-F.... (RAL-colours, other colours on request)




#### Mixing ratio by weight

7:1 with curing agent DZ-13



Demineralised water

### WIEREGEN-DW54 / Guideline

	Density (g/mL)	Solid content (weight %)	VOC-content (weight %)	Solid content by volume	
				(%)	(mL/kg)
	1.3	62.5	< 3.0	51.0	395
	DFT * (µm)	Calculated wet-film thickness (µm)	Consumption (kg/m <sup>2</sup> )	Spreading rate (m <sup>2</sup> /kg)	
	80	157	0.205	4.9	

## COMMENTS ON PROCESSING

Recommendation at temperatures of approx. 20 °C



Airless/  
Airmix



High  
pressure



Roller/Brush  
application




	Airless/ Airmix	High pressure	Roller/Brush application
<b>Application viscosity (s)</b> (6 mm DIN-cup)	20 to 30	10 to 15	20 to 30
<b>Nozzle diameter (mm)</b>	0.33 to 0.58	1.5 to 1.8	-
<b>Material pressure (bar)</b>	120 to 200	-	-
<b>Atomiser pressure (bar)</b>	-	4.0 to 5.0	-
<b>DFT * per working operation (µm)</b>	80	80	40 to 60
<b>Addition of thinner (%)</b>	0 to 3	3 to 6	0 to 3



#### Pot life

2 hours at 20 °C (relating to temperature)

\* DFT = Dry Film Thickness

Drying/Curing times at 80 µm DFT		Ambient air temperature 20 °C
	touch dry:	after 50 minutes
	tack free:	after approx. 4 hours
	ready for overcoating/handling:	after approx. 10 hours

## INSTRUCTIONS FOR APPLICATION

### Surface preparation

#### Steel surfaces and cast iron

- Remove adhesion-reducing substances e. g. cleaning, washing, phosphating, alternatively
- Blast cleaning Sa 2 ½ according to EN ISO 12944-4, Roughness grade medium (G) according to EN ISO 8503-1

#### Strip galvanised steel surfaces and aluminium/cast aluminium

- Remove adhesion-reducing substances, e. g. cleaning, washing, alternatively
- Chemical conversion layer (chromate, chromate free, phosphating)



**Air and surface temperature**  
10 to 40 °C



Relative humidity ≤ 80 %  
Dew point distance ≥ 3 °C

## PAINT SYSTEMS

### EXAMPLES

		Product(s) (other paint systems on request)
	<b>Priming coats</b>	GEHOPON-EW18-Metallgrund GEHOPON-EW19-Metallgrund GEHOTEX-W92-Metallgrund
	<b>Monolayer / Top coat</b>	WIEREGEN-DW54

## SAFETY MEASURES



The relevant data can be found in the current material safety data sheets, available at [www.geholit-wierner.de](http://www.geholit-wierner.de).

The statements made here are based on the present state of our knowledge. We do not assume liability for damages resulting from the use of the material or from any advice given by our employees. In this respect, any advice given by our employees has to be seen as not binding. The processor is responsible for the supervision or construction, the maintaining of process guidelines and the observation of the established rules of techniques, even if our employees are present at the time our material is being applied. This information is subject to modifications due to technical improvements. The latest edition of this information replaces all previous issues.